



Midwest Fasteners
 450 Richard St.
 Miamisburg, OH 45342
 Website: www.midwestfasteners.com

Toll Free: (800) 852-8352
 Phone: (937) 866-0463
 Fax: (937) 866-4174
 Email: sales@midwestfasteners.com

[All Categories](#) > [Weld Studs](#) > [Arc Weld Studs](#) > [Bent Collar Arc Weld Studs](#)

BENT COLLAR ARC WELD STUDS

TD	Std. TL	Min. BL	BD	CD	CT	X
3/8-16	1.375	0.625	0.331	5/8	0.109	5/8

Materials

Low Carbon Steel

C - 0.23% max. P - 0.04% max.
 Mn - 0.90% max. S - 0.05% max.

Stainless Steel

AlSI grade - 302/304/305 std.
 Other grades available upon request.

Mechanical Properties

Low Carbon Steel

Tensile - 60,000 psi (min.)
 Yield - 50,000 psi (min.)
 Elongation - 20% (in 2 inches)

Stainless Steel

Values for various grades available upon request.

Plating

Low Carbon Steel

Plating is not standard.
 Copper, nickel, and zinc available upon customer request.

Stainless Steel

Does not apply to Stainless.

Ferrules

Ferrules are component parts of studs. Not sold separately.


Threads

Standard thread is UNC-2A (Rolled when possible), other threads are available upon request.
 Maximum standard thread length is 3-7/8".

Please click the [Request Information](#) button to configure your Bent Collar Arc Weld Studs.

[less](#)

Arc
Weld
Studs



Ferrules

Ferrules	Code	B	D	E	M	Part No.
	C375	0.785	0.875	0.125	0.250	092 0014 08