

OP-SIL RTV 1001
(ACETOXY)

OPTICALLY CLEAR SEALANT

1-PART HIGH PERFORMANCE INDUSTRIAL /
CONSTRUCTION GRADE SILICONE SEALANT**SPECIFIC APPLICATIONS**

Lens covers, light fixtures, window glazing seals, bathroom clear shower walls, mirrors, rear window slider windows, skylights, protective coating for all glass sealing needs.

PHYSICAL PROPERTIES

Cure System	Acetoxy
Physical Properties (cured)	Rubber
Specific Gravity	1.05
Extrusion Rate, g/min.	450
Temperature Range	-62° to 200° F
Intermittent Temperature Range	230° F
Skin Over Time (min)	8*
Tack Over Time (min)	10*
Cure Time (hours)	24
Tensile Strength (psi)	300
Elongation %	400
Durometer Shore A	25
Dielectric Strength kv/mm (v/mil)	20 (500)
Dielectric Constant at Hz	3.5 @ 60
Shelf Life (months)	12

* All properties derived from lab conditions, (77° F at 50% relative humidity)

AVAILABLE COLORS: Optically clear

PACKAGING: 10.3 fl. oz. cartridges
5 gallon pails
55 gallon drums



SILCO INC.
Application Driven Silicone