

LINACOUSTIC® R-300 COATED RIGID FIBERGLASS PLENUM LINER BOARD

DATA SHEET

DESCRIPTION

Linacoustic® R-300 is a rigid fiber glass board that meets or exceeds all ASTM C1071 Type II duct liner requirements. The airstream surface and the long edges are coated with the tough, smooth, state-of-the-art acrylic polymer, Permacote®. R-300 offers exceptional durability and superior acoustical and thermal performance.

USES

R-300 is specifically designed for use as an extended performance lining insulation for HVAC plenums and air distribution ductwork.

STORAGE

Linacoustic R-300 should be kept clean and dry during storage, transport, fabrication, installation, and system operation.

GENERAL PROPERTIES

STANDARD THICKNESSES AND PACKAGING

Thickness		Width		Length	Length		
in	mm	in	mm	in	mm		
1	25	48	1219	96	2438		
11/2	38	48	1219	96	2438		
2	51	48	1219	96	2438		
3	76.2	48	1219	96	2438		
4	101.6	48	1219	96	2438		

Non-standard sizes up to 4" (102 mm) thickness and 120" (3.1 m) lengths available on special request.

Maximum Flame Spread Index

Maximum Smoke Developed Index

SURFACE BURNING CHARACTERISTICS

Linacoustic R-300 meets the Surface Burning Characteristics and Limited Combustibility of the following standards:

Standard/Test Method

- ASTM E84
- UL 723
- NFPA 255
- NFPA 90A and 90B
- NFPA 259
- CAN/ULC S102

UL labels supplied on packages when requested on order.

SPECIFICATION COMPLIANCE

- ASTM C1071, Type II
- ASHRAE 62
- MEA# 353-93-M
- SMACNA Application Standards for Duct Liners
- NAIMA Fibrous Glass Duct Liner Installation Standard
- Canada: CGSB 51.10-92

SUSTAINABLE BUILDING ATTRIBUTES

GREENGUARD® certification is not intended for residential environments. Instead, the certification is intended only for buildings meeting ASHRAE 62.1-2007 commercial building ventilation rates. This certification is proof that the product meets the GREENGUARD Environmental Institute's indoor air quality standards and product emission standards for VOCs.



25

50



ADVANTAGES

Improves Indoor Building Environment. Permacote Linacoustic R-300 helps improve indoor environmental quality by helping to control both temperature and sound.

Absorbs Disturbing Sound. Permacote Linacoustic R-300 has exceptional soundabsorbing properties far exceeding the requirements of ASTM C1071. Ducttransmitted noise, such as crosstalk and sound energy from air movement and mechanical equipment, is noticeably reduced.

Resistant to Dust and Dirt. The tough, acrylic polymer Permacote coating helps guard against incursion of dust or dirt into the substrate, minimizing the potential for biological growth.

Will Not Support Microbial Growth. Permacote coating is formulated with an immobilized, EPA-registered, protective agent to protect the coating from potential growth of fungus and bacteria.

Permacote Linacoustic R-300 passes ASTM C1071 fungi testing, as well as the more stringent ASTM G-21. Bacteria tests were conducted in accordance with ASTM G-22. Detailed information is available in Johns Manville fact sheet HSE-103FS.

Note: As with any type of surface, microbial growth may occur in accumulated duct system dirt, given certain conditions. This risk is minimized with proper design, filtration, maintenance and operation of the HVAC system.

Withstands High Velocity. Permacote Linacoustic R-300 has been tested to the recommended maximum velocity of 6,000 fpm (30.5 m/sec). Fiber erosion test results were determined using the Isokinetic Sampling Method described in Johns Manville Fiber Erosion Testing Fact Sheet HSE-133FS.

Cleanability. If necessary, the surface may be cleaned using standard industryrecognized dry methods. See the North American Insulation Manufacturers Association (NAIMA) "Cleaning Fibrous Glass Insulated Air Duct Systems."

Resists Damage. The specially designed Permacote airstream surface enhances the ability of R-300 to resist damage from typical in-shop handling, fabrication and jobsite shipment.

LINACOUSTIC® R-300

COATED RIGID FIBERGLASS PLENUM LINER BOARD

DATA SHEET

INSTALLATION

All portions of duct designated to receive duct liner should be completely covered with Permacote Linacoustic R-300. The smooth, black Permacote surface of the Linacoustic R-300 must face the airstream. All Permacote Linacoustic R-300 should be cut to ensure tight, overlapped corner joints. The top pieces should be supported by the side pieces.

Permacote Linacoustic R-300 must be adhered to the sheet metal with full coverage of an approved adhesive that meets ASTM C-916, and all exposed leading edges and transverse edges should be coated with Johns Manville SuperSeal® HV, Johns Manville SuperSeal® Edge Treatment, or an approved adhesive.

The Permacote Linacoustic R-300 must be additionally secured with mechanical fasteners spaced per the schedule shown in the diagram below. The pin length should be such as to hold the material firmly in place with minimum compression of the material

All material must be installed in accordance with the NAIMA Fibrous Glass Duct Liner Installation Standard.

THERMAL PERFORMANCE

		III OIIII/IIIICE				
THI	CKNESS	R-VALUE		CONDUCTANCE		
in	mm	(HR•FT²•°F)/BTU	M ² •°C/W	BTU/(HR•FT ² •°F)	W/M²•°C	_
1	25	4.3	0.76	0.23	1.31	_
1½	38	6.3	1.11	0.16	0.91	
2	51	8.7	1.53	0.12	0.68	
3	76.2	13.0	2.34	0.08	0.43	
4	101.6	17.4	3.13	0.06	0.32	


R-value and conductance are calculated from the material thermal conductivity tested in accordance with ASTM C518 at 75°F (24°C) mean temperature.

SOUND ABSORPTION COEFFICIENTS (TYPE "A" MOUNTING)

SOUND ABSORPTION COEFFICIENT AT FREQUENCY

THIC	KNESS	(CYCLI	S PER S	ECOND) (JF:				
in	mm	125	250	500	1000	2000	4000	NRC	_
1	25	0.04	0.26	0.69	1.00	1.07	1.02	0.75	_
1½	38	0.14	0.52	1.01	1.07	1.03	0.97	0.90	
2	51	0.26	0.73	1.10	1.10	1.04	1.03	1.00	
3	76.2	0.56	1.18	1.24	1.12	1.04	1.03	1.15	
4	101.6	0.81	1.30	1.26	1.12	1.04	1.05	1.20	

Coefficients were tested in accordance with ASTM C423 and ASTM E795.



When velocity exceeds 4000 fpm (20.3 m/sec), use metal nosing on every leading edge. Nosing may be formed on duct or be channel or zee attached by screws, rivets or welds. A metal nosing shall also be installed at the fan dis-charge and at any point where lined duct is preceded by unlined duct.

Duct Section (Typically 4' or 5' [1.22 m or 1.52 m])



Maximum Spacing for Fasteners. Actual Intervals Are Approximate.

Dimensions

Velocity*	А		В		С		D	
velocity	in	mm	in	mm	in	mm	in	mm
0 - 2500 fpm (0 - 12.7 m/sec)	3	76	12	305	4	102	18	457
2501 – 6000 fpm (12.7 – 30.5 m/sec)	3	76	12	305	4	102	18	457

^{*}Unless a lower level is set by the listing agency.

Liner adhered to the duct with 90% minimum area coverage of adhesive. Adhesive shall conform to ASTM C916.

Shop or field cuts shall be liberally coated with SuperSeal Edge Treatment or approved adhesive.

RECYCLED CONTENT



ISO 9000 CERTIFICATION

Johns Manville mechanical insulation products are designed, manufactured and tested in our own facilities, which are certified and registered to stringent ISO 9000 (ANSI/ASQC 90) series quality standards. This certification, along with regular, independent third-party auditing for compliance, is your assurance that Johns Manville products deliver consistent high quality.



717 17th St. Denver, CO 80202 800-654-3103 www.JM.com

North American Sales Offices, Insulation Systems

Eastern Region & Canada

P.O. Box 158 Defiance, OH 43512 800-334-2399 Fax: 419-784-7866

Western Region & Outside North America

P.O. Box 5108 Denver, CO 80217 800-368-4431 Fax: 303-978-4661 Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of Linacoustic® R-300 listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit www.jm.com/terms-conditions or call (800)654-3103.