ALPHA ASSOCIATES, INC.

ALPHA - MARITEX STYLE 8459-2-SS

145 LEHIGH AVENUE LAKEWOOD, N.J. 08701 Phone: (732) 634-5700 Fax: (732) 634-1430

DESCRIPTION

Alpha Maritex Style 8459-2-SS is a fiberglass fabric impregnated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This product is designed specifically for high temperature (500 ° F) removable pads, flange and valve covers. This product can be manufactured to meet the requirements of NRC 1.36 as well as MIL-I-24244. This (Heavy Duty) silicone impregnated fiberglass fabric is used where more wear and tear is needed.

ADVANTAGES

Aluminum color, Water and Oil resistant, Acid and Alkali resistant, Flame retardant, Low Smoke, Easily sewn, Adhesive bonded or sealed. The special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tear and puncture.

APPLICATIONS

Removable Insulation Pad Covering, Flange and Valve covers, Welding Curtains and Splash Shields, Safety Clothing, Equipment Covers, Flexible Connectors (Expansion Joints).

PROPERTY DATA STYLE 8459-2-SS

<u>CHARACTERISTIC</u>	<u>METHOD</u>	<u>VALUES*</u>		
		<u>ENGLISH</u>	<u>1</u>	<u>METRIC</u>
WEIGHT	ASTM-D-3776	34.0 oz/sy ± 10%		1156 g/m² ± 10%
THICKNESS	ASTM-D-1777	0.037" ± 10%		0.940 mm ± 10%
TENSILE STRENGTH	ASTM-D-5034	Warp- 400 lbs/ind Fill- 350 lbs/ind		71.44 kg/cm 62.51 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp- 65 lbs min. Fill- 55 lbs min.		29.48 kg 24.95 kg
BURST STRENGTH	ASTM-D-3786	750 psi min.		52.5 kg/cm²
FLAME RESISTANCE	FED 191/5903.2	Char Length 1 inch ma	ax.	2.54 cm max.
		Afterglow 1 second	max.	1 second max.
		Flame Out 1 second	max.	1 second max.
TEMPERATURE RESISTANCE	FED SPEC HHB-100B	-67 °F to +500 °F		-55 °C to 260 °C
BASE FABRIC and WEAVE		Fiberglass/Satin Weave		
COLOR and COATING		Silver Silicone		

DATA SHEET 13431

REV F DATE: 9/16/09

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.

^{*} All values are nominal unless otherwise specified.